	BUILDING RESEARCH INSTITUTE	
LT	**TEST REPORT NO. LT-1192/08/2**	**Page 1/1**

FINISHING MATERIALS TESTING LABORATORY
Address: 00-611 Warszawa ul. Filtrowa 1, telephone nr. (0-22) 825-04-71 extension tel. 223

CLIENT: BARLINEK INWESTYCJE Sp. z o. o.
ul. Przemysłowa 1, 74-320 Barlinek

PRODUCT/~~OBJECT~~: Three-layer floor board OAK; manufacturer Barlinek Inwestycje POLSKA

received/~~taken~~ to test on 15 November with the report no. LS-555/08
examined from 27 January 2009 to 29 January 2009

METHOD/PROCEDURE OF EXAM: **PN-EN 14342:2008** and **CEN/TS 15676:2007**

RESULTS OF THE EXAMINATION:

Examined feature	Results of the examination
Resistance to slipperiness **USRV**	
- dry surface	average **99** ± 3
- humid surface	average **22** ± 1

ANOTHER INFORMATION RELATING TO EXAMINATION:
Information relating to examined floor board:
1. name of the product: three-layer floor board OAK
2. thickness of the product – 10mm
3. thickness of the frontal layer – 2,5mm
4. inner layer – coniferous wood with HDF insert
5. bottom layer – coniferous wood
6. finish – open-pores varnish
7. product's code – 108589

Person responsible for examination:	Person who authorized the report:
inż. Andrzej Nowacki	**mgr inż. Jacek Popczyk**
.....	.....
signature	**signature**

Warszawa, 29 of January 2009

Testing Laboratory declare, that the test results apply only to examined object. Without written permission of Testing Laboratory Report cannot be duplicate differently from as a whole. Test report is not the document to trade admission and to common use in building.